

# 14-ABCD-189-NOIRMOUTIER-B



#### Size Board LENGTH 1860 mm WIDTH 189 mm **TOTAL THICKNESS** 14 mm THICKNESS TOP 3 mm Min. 7 Pl. x

PLANK QUANTITY

Size <b>Pack</b>	
PACK LENGTH	1870 mm
PACK WIDTH	200 mm
PACK THICKNESS	120 mm
PACK WEIGHT	23 kg
LAYERS/PACK	8
M <sup>2</sup> /PACK	2.81 m <sup>2</sup>

Size Pallet	
LENGTH PALLET	1890 mm
WIDTH PALLET	1000 mm
HEIGHT PALLET	1080 mm
WEIGHT PALLET	935 kg
PACKS/PALLET	40
M <sup>2</sup> /PALLET	112.4 m <sup>2</sup>

### Characteristics

Top layer	
WOOD SPECIES	Oak
LATIN NAME	Quercus Mongolica
GRADE	ABCD
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	3 mm
STRIPS	1 strip
CUTTING METHOD	Sawn veneer
BEVEL	Two long sides (0,75 mm)
COLOUR FINISH	Smoked Natural lacquer
SURFACE STRUCTURE	Brushed

1860 mm

## Composition of the support

SUPPORT TYPE	Poplar support and backing
WOOD SPECIES SUPPORT	Poplar
SUPPORT CONSTRUCTION	2-layer (Support, balancer)
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Crosswise (Casco)

## Installation

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Drop click system	Light household use	Yes
×	Moderate commercial use	RESANDABLE
Normal commercial use		The thickness of the upper layer allows resanding the floor, but this
	Normal household use	may influence the floor structure.
	Intensive commercial use	



## 14-ABCD-189-NOIRMOUTIER-B

#### Certification

This product conforms to CE standard EN 14342:2005 + A1:2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1  $\,$
- Does not contain any PCP (pentachlorophenol)

# Technical specifications

- Hardness: N / mm <sup>2</sup> (Birnell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

#### Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)