



#### Size Board

<b>LENGTH</b>	1900 mm
<b>WIDTH</b>	190 mm
<b>TOTAL THICKNESS</b>	14 mm
<b>THICKNESS TOP LAYER</b>	3 mm
<b>PLANK QUANTITY</b>	Min. 7 Pl. x 1900 mm

#### Size Pack

<b>PACK LENGTH</b>	1910 mm
<b>PACK WIDTH</b>	200 mm
<b>PACK THICKNESS</b>	120 mm
<b>PACK WEIGHT</b>	24 kg
<b>LAYERS/PACK</b>	8
<b>M<sup>2</sup>/PACK</b>	2.89 m <sup>2</sup>

#### Size Pallet

<b>LENGTH PALLET</b>	1930 mm
<b>WIDTH PALLET</b>	1000 mm
<b>HEIGHT PALLET</b>	1080 mm
<b>WEIGHT PALLET</b>	975 kg
<b>PACKS/PALLET</b>	40
<b>M<sup>2</sup>/PALLET</b>	115.6 m <sup>2</sup>

## Characteristics


### Top layer

<b>WOOD SPECIES</b>	Oak
<b>LATIN NAME</b>	Quercus Robur
<b>GRADE</b>	CLASSIC
<b>CONSTRUCTION</b>	3-layer
<b>THICKNESS TOP LAYER</b>	3 mm
<b>STRIPS</b>	1 strip
<b>CUTTING METHOD</b>	Sawn veneer
<b>BEVEL</b>	Two long sides (0,75 mm)
<b>COLOUR FINISH</b>	Stained Brushed Invisible oiled
<b>SURFACE STRUCTURE</b>	Brushed

### Composition of the support

<b>SUPPORT TYPE</b>	Poplar support and backing
<b>WOOD SPECIES SUPPORT</b>	Poplar
<b>SUPPORT CONSTRUCTION</b>	2-layer (Support, balancer)
<b>TOTAL THICKNESS SUPPORT</b>	11 mm
<b>ADHESION</b>	Crosswise (Casco)

## Installation

<b>SYSTEM</b>	<b>APPLICATIONS</b>	<b>UNDERFLOOR HEATING</b>
Tongue and groove system	Light household use Moderate commercial use	Yes
	Take the necessary precautions for use in wet areas Normal commercial use Normal household use Intensive commercial use	<b>RESANDABLE</b> The thickness of the upper layer allows resanding the floor, but this may influence the floor structure.

**Certification**

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

**Technical specifications**

- Hardness: N / mm<sup>2</sup> (Birrell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W