

#### 15-CLASSIC-189-BERGERAC



## Size Board LENGTH 1860 mm WIDTH 189 mm

THICKNESS TOP 4 mm

PLANK QUANTITY Min. 7 Pl. x 1860 mm

#### Size **Pack**

PACK LENGTH	1870 mm
PACK WIDTH	200 mm
PACK THICKNESS	130 mm
PACK WEIGHT	25 kg
LAYERS/PACK	8
M <sup>2</sup> /PACK	2.81 m <sup>2</sup>

#### Size Pallet

LENGTH PALLET	1890 mm
WIDTH PALLET	1000 mm
HEIGHT PALLET	1160 mm
WEIGHT PALLET	1015 kg
PACKS/PALLET	40
M <sup>2</sup> /PALLET	112.4 m <sup>2</sup>

#### **Characteristics**

#### Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Mongolica
GRADE	CLASSIC
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	4 mm
STRIPS	1 strip
CUTTING METHOD	Sawn veneer
BEVEL	Micro bevel Four sides (0,50 mm)
COLOUR FINISH	Smoked Natural oiled
SURFACE STRUCTURE	Structured


#### Composition of the support

SUPPORT TYPE	Poplar support and backing
WOOD SPECIES SUPPORT	Poplar
SUPPORT CONSTRUCTION	2-layer (Support, balancer)
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Crosswise (Casco)

#### Installation

# Tongue and groove system Light household use Moderate commercial use Normal commercial use Normal household use UNDERFLOOR HEATING Yes RESANDABLE The thickness of the upper layer allows resanding the floor, but this may influence the floor structure.

Intensive commercial use



#### 15-CLASSIC-189-BERGERAC

#### Certification

This product conforms to CE standard EN 14342:2005 + A1:2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1  $\,$
- Does not contain any PCP (pentachlorophenol)

### Technical specifications

- Hardness: N / mm <sup>2</sup> (Birnell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

#### Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)