

# 15-CLASSIC-190-BARN-SAUVIGNON-B



# Size Board LENGTH 1900 mm WIDTH 190 mm TOTAL THICKNESS 15 mm THICKNESS TOP LAYER 4 mm PLANK QUANTITY Min. 7 Pl. x 1900 mm

Size <b>Pack</b>	
PACK LENGTH	1910 mm
PACK WIDTH	200 mm
PACK THICKNESS	130 mm
PACK WEIGHT	26 kg
LAYERS/PACK	8
M <sup>2</sup> /PACK	2.89 m²

Size <b>Pallet</b>	
LENGTH PALLET	1930 mm
WIDTH PALLET	1000 mm
HEIGHT PALLET	1160 mm
WEIGHT PALLET	1055 kg
PACKS/PALLET	40
M <sup>2</sup> /PALLET	115.6 m²

#### Characteristics


WOOD SPECIES	Oak
LATIN NAME	Quercus Mongolica
GRADE	CLASSIC
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	4 mm
STRIPS	1 strip
CUTTING METHOD	Axe split
BEVEL	Distressed bevel (0,50 mm) to short and long sides
COLOUR FINISH	Stained Smoked 2-component oiled
SURFACE STRUCTURE	Brushed

### Composition of the support

SUPPORT TYPE	Poplar support and backing
WOOD SPECIES SUPPORT	Poplar
SUPPORT CONSTRUCTION	2-layer (Support, balancer)
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Crosswise (Casco)

#### Installation

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove system	Light household use	Yes
	Moderate commercial use	RESANDABLE
	Normal household use	Not resandable



## 15-CLASSIC-190-BARN-SAUVIGNON-B

#### Certification

This product conforms to CE standard EN 14342:2005 + A1:2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1  $\,$
- Does not contain any PCP (pentachlorophenol)

# Technical specifications

- Hardness: N / mm <sup>2</sup> (Birnell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

#### Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)