

15-CLASSIC-220-RELIEF-PINOTBLANC



Size **Board**

LENGTH	2200 mm
WIDTH	220mm
TOTAL THICKNESS	15 mm
THICKNESS TOP LAYER	4 mm
PLANK QUANTITY	Min. 5 Pl. x

Size **Pack**

PACK LENGTH	2210 mm
PACK WIDTH	230 mm
PACK THICKNESS	115 mm
PACK WEIGHT	30 kg
LAYERS/PACK	6
M²/PACK	2.90 m ²

Size Pallet

LENGTH PALLET	2230 mm
WIDTH PALLET	1000 mm
HEIGHT PALLET	1040 mm
WEIGHT PALLET	1215 kg
PACKS/PALLET	40
M ² /PALLET	116 m²

Characteristics

Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	CLASSIC
CONSTRUCTION	2-layer
THICKNESS TOP LAYER	4 mm
STRIPS	1 strip
CUTTING METHOD	Sawn veneer
BEVEL	Micro bevel Two long sides (0,50 mm)
COLOUR FINISH	Invisible oiled
SURFACE STRUCTURE	Structured

Composition of the support

SUPPORT TYPE	Multiplex support
WOOD SPECIES SUPPORT	Mixed Light Hardwood
SUPPORT CONSTRUCTION	Multiplex (8 layers)
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Crosswise (Casco)

Installation

SYSTEM

Tongue and groove system



APPLICATIONS

Light household use

Moderate commercial use

Normal commercial use

Normal household use

Intensive commercial use


UNDERFLOOR HEATING

Yes

RESANDABLE

The thickness of the upper layer allows resanding the floor, but this may influence the floor structure.

[©] This fact sheet was written by Labeco BVBA, Warandestraat 37-39, B-9810 NAZARETH. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



15-CLASSIC-220-RELIEF-PINOTBLANC

Certification

This product conforms to CE standard EN 14342:2005 + A1:2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm ² (Birnell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)