



Size Board

| | |
|---------------------|----------------------|
| LENGTH | 2200 mm |
| WIDTH | 260 mm |
| TOTAL THICKNESS | 15 mm |
| THICKNESS TOP LAYER | 4 mm |
| PLANK QUANTITY | Min. 3 Pl. x 2200 mm |

Size Pack

| | |
|----------------------|---------------------|
| PACK LENGTH | 2210 mm |
| PACK WIDTH | 270 mm |
| PACK THICKNESS | 70 mm |
| PACK WEIGHT | 20 kg |
| LAYERS/PACK | 4 |
| M ² /PACK | 2.29 m ² |

Size Pallet

| | |
|------------------------|---------------------|
| LENGTH PALLET | 2230 mm |
| WIDTH PALLET | 1080 mm |
| HEIGHT PALLET | 820 mm |
| WEIGHT PALLET | 815 kg |
| PACKS/PALLET | 40 |
| M ² /PALLET | 91.6 m ² |

Characteristics

Top layer

| | |
|---------------------|--|
| WOOD SPECIES | Oak |
| LATIN NAME | Quercus Robur |
| GRADE | CLASSIC |
| CONSTRUCTION | 3-layer |
| THICKNESS TOP LAYER | 4 mm |
| STRIPS | 1 strip |
| CUTTING METHOD | Sawn veneer |
| BEVEL | Distressed bevel (0,50 mm) to short and long sides |
| COLOUR FINISH | Smoked White oiled |
| SURFACE STRUCTURE | Antique effect |

Composition of the support

| | |
|-------------------------|-----------------------------|
| SUPPORT TYPE | Poplar support and backing |
| WOOD SPECIES SUPPORT | Poplar |
| SUPPORT CONSTRUCTION | 2-layer (Support, balancer) |
| TOTAL THICKNESS SUPPORT | 11 mm |
| ADHESION | Crosswise (Casco) |

Installation

SYSTEM

Tongue and groove system



APPLICATIONS

Light household use
Moderate commercial use
Normal commercial use
Normal household use
Intensive commercial use

UNDERFLOOR HEATING

Yes

RESANDABLE

The thickness of the upper layer allows resanding the floor, but this may influence the floor structure.

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm² (Birrell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)