

**Size Board**

LENGTH	220 mm
WIDTH	190 mm
TOTAL THICKNESS	15 mm
THICKNESS TOP LAYER	4 mm

Size Pack

PACK LENGTH	750 mm
PACK WIDTH	200 mm
PACK THICKNESS	130 mm
PACK WEIGHT	11 kg
LAYERS/PACK	24
M²/PACK	1 m ²

Size Pallet

LENGTH PALLET	2270 mm
WIDTH PALLET	1000 mm
HEIGHT PALLET	1000 mm
WEIGHT PALLET	807 kg
PACKS/PALLET	72
M²/PALLET	72 m ²

Characteristics**Top layer**

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	ABC
CONSTRUCTION	2-layer
THICKNESS TOP LAYER	4 mm
CUTTING METHOD	Sawn veneer
BEVEL	Micro bevel Four sides (0,50 mm)
COLOUR FINISH	Unfinished
SURFACE STRUCTURE	Smooth

Composition of the support

SUPPORT TYPE	Multiplex support
WOOD SPECIES SUPPORT	Mixed Light Hardwood
SUPPORT CONSTRUCTION	Multiplex (7 layers)
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Crosswise (Casco)

Installation**SYSTEM**

Tongue and groove system

**APPLICATIONS**

Light household use
 Moderate commercial use
 Normal commercial use
 Normal household use
 Intensive commercial use

UNDERFLOOR HEATING

No

RESANDABLE

Resandable

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm² (Birrell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)