



Size Board

LENGTH	2200 mm
WIDTH	220 mm
TOTAL THICKNESS	21 mm
THICKNESS TOP LAYER	6 mm
PLANK QUANTITY	Min. 3 Pl. x 2200 mm

Size Pack

PACK LENGTH	2210 mm
PACK WIDTH	230 mm
PACK THICKNESS	95 mm
PACK WEIGHT	28 kg
LAYERS/PACK	4
M²/PACK	1.94 m ²

Size Pallet

LENGTH PALLET	2230 mm
WIDTH PALLET	920 mm
HEIGHT PALLET	1070 mm
WEIGHT PALLET	1135 kg
PACKS/PALLET	40
M²/PALLET	77.6 m ²

Characteristics

Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	AB
CONSTRUCTION	2-layer
THICKNESS TOP LAYER	6 mm
STRIPS	1 strip
CUTTING METHOD	Sawn veneer
BEVEL	Micro bevel Two long sides (0,50 mm)
COLOUR FINISH	Unfinished
SURFACE STRUCTURE	Smooth

Composition of the support

SUPPORT TYPE	Multiplex support
WOOD SPECIES SUPPORT	Mixed Light Hardwood
SUPPORT CONSTRUCTION	Multiplex (11 layers)
TOTAL THICKNESS SUPPORT	15 mm
ADHESION	Crosswise (Casco)

Installation

SYSTEM

Tongue and groove system



APPLICATIONS

Light household use
Moderate commercial use
Normal commercial use
Normal household use
Intensive commercial use

UNDERFLOOR HEATING

Yes

RESANDABLE

Resandable

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm² (Birrell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)